



# Technical Data Sheet

## Super Set 942

### **Product Features:**

Super Set 942 Furan Nobake Resin is a zero nitrogen, zero water furan resin that offers a number of features that set it apart from conventional furan resins on the market. The following product features characterize this binder:

- Zero Water, Zero Nitrogen
- Zero Free Formaldehyde and Zero Phenol
- Very Low Viscosity
- High Tensile Strength
- Exceptional Sand Reclaimability
- No Modifiers or Extenders

### **Product Description:**

Super Set 942 is a thermosetting furan resin that is used in conjunction with an acid catalyst which, when mixed with sand, undergoes a condensation reaction to form a cured polymer. Typically the amount of Super Set 942 resin applied to the sand will range between 0.8% to 1.2% resin, based on the weight of the sand. The quantity of acid used in the sand mix is dependent upon the type and strength of the acid, but normally ranges between 20% - 50% based on the weight of the resin.

Recommended practice when using Super Set resins is to start with a clean, washed and dried silica sand. Reclaimed sands are also widely used with this type of product. If mechanically reclaimed sand is used, sand that is low in fines and residual binder (Loss on Ignition) is preferred. In continuous or batch-type mixers, the acid should be the first component added to the sand, with the resin added after the acid has been dispersed. Caution should be exercised to prevent the liquid resin and acid components from coming into direct contact with one another since the resulting reaction can be very exothermic.

SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION BY SELLER, except that the product shall conform to contracted specifications, and that the product does not infringe any valid United States patent. The information provided herein was believed by Seller to be accurate at the time of preparation or prepared from sources believed to be reliable but it is the responsibility of the user to investigate and understand other pertinent sources of information to comply with all laws and procedures applicable to the safe handling and use of product and to determine the suitability of the product for its intended use. Buyers exclusive remedy shall be for damages and no claim of any kind, whether to product delivered or for non-delivery of product and whether based on contract, breach of warranty, negligence or otherwise shall be greater in amount than the purchase price of the quantity of product in respect of which damages are claimed. In no event shall Seller be liable for incidental or consequential damages, whether Buyer's claim is based on contract, breach of warranty, negligence or otherwise.

The typical properties of the Super Set 942 are defined in the table below.

<b>Typical Properties – Super Set 942</b>	
<b>Viscosity, cps</b>	7
<b>% Water</b>	0.2
<b>% Nitrogen</b>	0
<b>% Free Formaldehyde</b>	0
<b>% Furfuryl Alcohol</b>	92

### **Storage Guidelines**

Recommended storage temperature is between 60 - 90 ° F. At lower temperatures, viscosity will increase, making pumping and mixing more difficult. At higher temperatures, shelf life can be adversely affected. Drum storage should be in a dry area, out of direct sunlight. Partially used drums should be tightly closed, to prevent contamination.

### **Safe Handling**

Chemically resistant gloves and eye protection should be used when handling or using chemical binders. Material Safety Data Sheets are available for all products. Drum labels also contain handling information. Furan resins will react in a violent exothermic reaction with the acid catalysts or other acids. Do not mix furan resin with any acid except on sand during use.

### **Technical Service**

Proper selection of a binder system that meets your specific needs is key to achieving maximum performance benefits. HA-International LLC provides in-depth technical assistance and a wide range of furan nobake resins and catalysts. For additional information relating to the selection of resins or catalysts, please contact your HA-International representative so that we may assist you in putting together a binder system and foundry team that will help you achieve your goals. Both our in-house and field experts are available to assist you with your most challenging foundry application.

10/6/03 DJH

## **HA International LLC**

**“The Best Total Solution”**

630 Oakmont Lane  
Westmont, IL 60559

Telephone (630) 575-5700 Fax (630) 575-5800