



Technical Data Sheet

04-6001 Technikoat

Product Features

04-6001 Technikoat is a water based high solids zircon refractory coating designed for heavy iron and steel castings. This coating offers maximum protection for metal section sizes in excess of four inches even with high head pressures.

04-6001 Technikoat exhibits excellent flow characteristics, which impart superior brush and swab (85-90 Baume'), flow coat (78-82 Baume') and spray (88-92 Baume') properties.

Product Description

Appearance: 04-6001 Technikoat is a white slurry.

Physical Characteristics

	<u>Typical</u>
Density (lb/gal):	20.0 - 20.25
% Solids:	76 - 77
Brookfield Viscosity (cP):	2200 - 4200

Application and Drying

	<u>Typical</u>
Density (lb/gal):	19.0 - 20.0
% Solids:	75 - 76
Brookfield Viscosity (cP):	2200 - 2800

Drying

04-6001 Technikoat can be air, torch or oven dried.

Storage Guidelines

Recommend using 04-6001 Technikoat within 90 days
Do not allow product to freeze

SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION BY SELLER, except that the product shall conform to contracted specifications, and that the product does not infringe any valid United States patent. The information provided herein was believed by Seller to be accurate at the time of preparation or prepared from sources believed to be reliable but it is the responsibility of the user to investigate and understand other pertinent sources of information to comply with all laws and procedures applicable to the safe handling and use of product and to determine the suitability of the product for its intended use. Buyers exclusive remedy shall be for damages and no claim of any kind, whether to product delivered or for non-delivery of product and whether based on contract, breach of warranty, negligence or otherwise shall be greater in amount than the purchase price of the quantity of product in respect of which damages are claimed. In no event shall Seller be liable for incidental or consequential damages, whether Buyer's claim is based on contract, breach of warranty, negligence or otherwise.