

# PRODUCT INFORMATION

## ENVIROSET® 3D JET RESIN

### PRODUCT FEATURES

Enviroset 3D Jet Resin, is a low viscosity thermosetting furan resin that has been specially manufactured for use in all 3D Printers for sand cores and molds and is suitable for use with all types of metal. This following product features characterize this binder:

- Contains no nitrogen
- Low water
- Non-reportable formaldehyde and phenol
- Low viscosity
- High tensile strength

### DESCRIPTION

Enviroset 3D Jet Resin is a thermosetting furan resin that will react in the presence of a strong acid catalyst at ambient temperatures to form a cured binder. The low viscosity resin has been specially manufactured for use in all sand core and mold 3D printers. This resin can be used to make castings with all types of metals.

Typically the amount of Enviroset 3D Jet Resin applied to the sand will range between 1.0% and 1.5% resin, based on the weight of the sand. The quantity of acid used in the sand mix is dependent upon the type and strength of the acid, but normally ranges between 18% and 24% based on the weight of the Enviroset 3D Jet Resin. Recommended acid catalysts (activator) for pre-treating the printing substrate are TW-40 for highest strength and TC-50 for fastest part cleaning and highest resolution.

Recommended practice when using Enviroset 3D Jet Resin is to start with a clean, washed, and dried silica sand or aggregate. The acid should be the first added and thoroughly mixed with the sand or aggregate. The resin is then injected through the print head onto the sand/substrate after the sand has been placed. Caution should be exercised to prevent the liquid resin and acid components from coming into the direct contact with one another since the resulting reaction can be very exothermic.

### TYPICAL PHYSICAL PROPERTIES

- Viscosity @ 25°C, cps <10
- % Water <1.0
- % Nitrogen 0
- % Free Formaldehyde 0
- % Furfuryl Alcohol 92
- Density, pounds per gallon 9.34

### PERFORMANCE CHARACTERISTICS

Measurable tensile strength begins to develop shortly after the Enviroset 3D Jet Resin is injected onto the sand mix containing the acid. The rate of strength development is related to the chemistry of the resin and the catalyst used. Tensile strength will vary due to the many factors known to affect binder performance: sand quality, sand temperature, mixing efficiency, etc.

## STORAGE GUIDELINES

Recommended storage temperature is between 60-90°F. At lower temperatures, viscosity will increase, making pumping and mixing more difficult. Freezing temperatures should be avoided. At higher temperatures, shelf-life can be adversely affected. Drum storage should be in a dry area, out of direct sunlight. Partially used drums should be tightly closed, to prevent contamination. The recommended stock rotation is six months when properly stored.

## SAFE HANDLING

Chemically resistant gloves and eye protection should be used when handling or using resins and acids. Material Safety Data Sheets are available for all products. Drum labels also contain handling information. Furan resins will react in a violent exothermic reaction with the acid catalysts or other acids. Do not mix furan resin with any acid except on sand during use. Refer to the Material Safety Data Sheet for additional information.

## TECHNICAL ASSISTANCE

HA International can help you optimize your operation, improve your performance, and help you choose components to meet all your core making needs. HA International will help you choose the right Part-1 to Part-2 ratios for your operation. Both our in-house and field experts are available to assist you with your most challenging foundry applications. Call your sales representative for additional technical information and to help you find the best binder to achieve your goals.

**FOR EMERGENCY MEDICAL ASSISTANCE PLEASE CALL:** Health & Safety Information Services: 1-866-303-6949

SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION BY SELLER, except that the product shall conform to contracted specifications, and that the product does not infringe any valid United States patent. The information provided herein was believed by Seller to be accurate at the time of preparation or prepared from sources believed to be reliable but it is the responsibility of the user to investigate and understand other pertinent sources of information to comply with all laws and procedures applicable to the safe handling and use of product and to determine the suitability of the product for its intended use. Buyer's exclusive remedy shall be for damages and no claim of any kind, whether to product delivered or for non-delivery of product and whether based on contract, breach of warranty, negligence or otherwise shall be greater in amount than the purchase price of the quantity of product in respect of which damages are claimed. In no event shall Seller be liable for incidental or consequential damages, whether Buyer's claim is based on contract, breach of warranty, negligence or otherwise.

07/28/18 – D.T.  
HA-International.com · 800-323-6863

The data within this document is for description purposes only. The information is not intended and may not be construed to represent a warranty of specific product or application properties or a warranty of usability for a specific purpose. Any statements about our products reflect our current state of knowledge and do not create any legally binding obligations. They do not limit any of the buyer's obligation under law or contract to test the delivered products for usability for the intended purpose. The safety data sheet must be observed. All product liability or warranty claims are explicitly excluded if the specific application of our product has not been approved by us. In addition our general terms and conditions for sales and delivery apply.